




Lube Control Pty Ltd
Providing lubrication solutions!

Unit 5/53 Norfolk Rd,
 Marion, SA 5043
 t: (08) 8298 5563
 f: (08) 8298 6253
 e: info@lubecontrol.com.au

OIL VISCOSITY CLASSIFICATION



5	Calcium 12-Hydroxy	FC	FC	FC	FC		SC	FC	FC	FC	FC	FC	FC
6	Calcium Complex	FC	NC	NC	NC	SC		NC	NC	NC	FC	FC	FC
7	Clay	NC	NC	NC	FC	FC	NC		NC	NC	NC	NC	NC
8	Lithium	FC	NC	NC	FC	FC	NC	NC		FC	FC	FC	FC
9	Lithium 12-Hydroxy	FC	NC	NC	SC	FC	NC	NC	FC		FC		FC
10	Lithium Complex	FC	FC	NC	FC	FC	FC	NC	FC	FC	FC		FC
11	Polyurea	SC	NC	NC	NC	NC	FC	NC	NC	NC	NC	NC	NC
12	Silica Gel	SC	FC	FC	?	?	NC	FC	?	?	FC		FC
13	Sodium	NC	SC	NC	NC	NC	NC	NC	SC	SC	SC	SC	SC

LEGEND

- FC Fully compatible
- SC Somewhat compatible - mixtures soften, but, remain soft
- NC Not compatible - mixtures soften severely and do not remain soft

All precautions were taken to ensure that the data in these tables are correct however, you should consult the manufacturer before mixing two different products

Lehla